

IN THE SPECIFICATION

Please amend the paragraph on page 19, lines 7-9, with the following amended paragraph:

The above components were mixed and thoroughly dispersed with a homomixer (jacket temperature: 35-40°C) for 20 minutes to obtain Coating Liquid (I) comprising a crosslinked silicone resin.

Please amend the paragraph on page 27, lines 2-4, with the following amended paragraph:

The above components were mixed and thoroughly dispersed with a homomixer (jacket temperature: 35-4.degree. C.) for 5 minutes to obtain Coating Liquid (II) comprising a crosslinked silicone resin.